

TECAPET natural - Stock Shapes

Chemical Designation

PET (Polyethylene terephthalate)

Colour

white

Density

1.38 g/cm³

Main features

- very good chemical resistance
- resistant to cleaning agents
- excellent wear properties
- excellent strength and stiffness
- low moisture absorption
- improved surface hardness
- resistance against high energy radiation

Target Industries

- food engineering
- engineering for beverage filling systems
- packaging and paper machinery
- semiconductor technology
- printing machines
- mechanical engineering
- pharmaceutical industry

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)		470,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	13000	psi	ASTM D 638	(2) Data obtained from public source
Elongation at yield	@ 73 °F	5	%	ASTM D 638	(3) Injection molded specimen
Elongation at break	@ 73 °F	20	%	ASTM D 638	(4) Injection molded specimen
Flexural strength	@ 73 °F	19000	psi	ASTM D 790	(5) Injection molded specimen
Modulus of elasticity (flexural test)	@ 73 °F	500,000	psi	ASTM D 790	
Compression modulus	@ 73 °F	392,000	psi	ASTM D 695	2)
Impact strength (Izod)	@ 73 °F	0.70	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale @ 73 °F	101		ASTM D 785	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.25	%	ASTM D 3702	3)
Coefficient of friction	Static	0.19	%	ASTM D 3702	4)
Wear rate	Against Steel, 40 psi, 50 fpm	2.10*10 ⁻⁷	in ³ -min/ft-lbs-hr	ASTM D 3702	5)
Thermal properties	condition	value		test method	comment
Melting temperature		490	°F	-	1) (1) Per ASTM D3418
Heat distortion temperature	@264 psi	175	°F	ASTM D 648	
Heat distortion temperature	@ 66 psi	240	°F	ASTM D 648	
Service temperature	Long Term	230	°F	-	
Service temperature	Intermittent	320	°F	-	
Thermal expansion (CLTE)		3.9*10 ⁻⁵	in/in/°F	ASTM D 696	
Specific heat		0.28	BTU/lb-F°	-	
Thermal conductivity		2.01	BTU-in/hr-ft ² -°F	-	
Electrical properties	condition	value		test method	comment
Volume resistivity		10 ¹⁵	Ω*cm	ASTM D 257	1) (1) Injection molded specimen
Dielectric strength		400	V/mil	ASTM D 149	2) (2) Injection molded specimen
Dissipation factor	@ 60 Hz, 73 °F	0.02	%	ASTM D 150	3) (3) Injection molded specimen
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.4	%	ASTM D 150	4) (4) Injection molded specimen
Other properties	condition	value		test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.10	%	ASTM D 570	(1) estimated
Moisture absorption	@ saturation, 73 °F	0.50	%	ASTM D 570	
Flammability (UL94)		HB	%	-	1)

→ Resin specification:
ASTM D5927-09 TPES0211
Shapes specification:
ASTM D 6261-10 S-TPES0211

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensinger-inc.com.