

### KYDEX® 100

High impact fire-rated sheet

#### Introduction

Super tough, durable KYDEX® 100, a proprietary alloy sheet, brings new dimensions to thermoformers in: formability, rigidity, breakage resistance, chemical resistance and fire retardancy.

## **General Information**

KYDEX® 100 is available in a wide range of standard and custom colours, textures, and sheet sizes. It is Underwriters Laboratories, Inc® recognized for UL Std 94 V-0, 5V and has 961 J/m (18 ft-lbs/in) Notched Izod impact resistance.

### Suggested Applications

Aircraft Interiors

- Medical Products
- Mass Transit Vehicle Interior Components
- Miscellaneous Applications

Equipment Housings

#### **Features**

- Good for deep or hard to form parts more rigid, parts will deform less when loaded
- High Notched Izod impact resistance offers unsurpassed resistance to breakage
- Meets highest standard for chemical resistance for thermoplastic materials
- Recognized by Underwriters Laboratories, Inc® for Std 94 V-0, 5V in all thicknesses and colours
- · Uniform wall thickness and crisp detail
- Easy machining and fabricating using conventional methods and equipment

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: http://www.sekisui-spi.com. For Material Safety Data Sheets, please call 800.325.3133.



88 Long Hill Cross Road, Shelton, Connecticut 06484 USA

ModernPlastics.com

sales@modernplastics.com

National Toll-Free: 800.243.9696

Phone: 203.333.3128 Fax: 203.333.4625



### KYDEX® 100 High impact fire-rated sheet

# Physical Properties

Property	Test Method	Typical Value <sup>1</sup>	
Specific Gravity	ASTM D-792	1.35	
Tensile Strength	ASTM D-638	42 MPa	6,100 psi
Elongation %	ASTM D-638	160	
Flexural Strength	ASTM D-790	63 MPa	9,100 psi
Modulus of Elasticity	ASTM D-790	2,310 MPa	335,000 psi
Notched Izod Impact Resistance, @ 23°C (73°F)	ASTM D-256	961 J/m	18 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	94	
Coefficient of Linear Thermal Expansion	ASTM D-696	7.56 x 10 <sup>-5</sup> °C	4.2 x 10 <sup>-5</sup> °F
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	78.3°C	173°F
Flammability: Underwriters Laboratories., Inc® Component Recognition	UL Standard 94 <sup>2</sup> UL Standard 746C	V-0, 5V <sup>3</sup>	
Motor Vehicle Safety Standard	MVSS 302	Pass	
Flammability: Vertical Burn, 60-second Vertical Burn, 12-second	FAR 25.853 (a)(i) FAR 25.853 (a)(ii)	PASS PASS	
BS 476 Part 7		Class 1 @ 3.20 mm Class 1Y @ 2.00mm	
EC 95 / 28 / EG		Pass (1.00 - 6.00mm)	
DIN 5510-2		0.90mm (S4, ST2, SR2) 6.50mm (S4, ST2, SR1)	

<sup>1</sup> Values based upon 3.18mm (0.125") sheet unless otherwise specified.

Not intended for specification purposes.



88 Long Hill Cross Road, Shelton, Connecticut 06484 USA

ModernPlastics.com

sales@modernplastics.com

National Toll-Free: 800.243.9696

Phone: 203.333.3128

Fax: 203.333.4625

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, ETHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.

<sup>2</sup> Underwriters Laboratories, Inc®, File E115252

<sup>3</sup> All thicknesses 0.71mm (0.028") and above

<sup>\*</sup> The thicknesses are added.