

KYDEX <sup>®</sup> V sheet is a recycled grade of a proprietary thermoplastic sheet that is cost competitive with other grades of thermoplastic sheet while offering improved performance.
KYDEX <sup>®</sup> V is particularly well suited for hidden or painted parts since it has some degress of color variability. It is only available in Black (52114), in thicknesses from 1.00mm (0.040") and up, and in a limited number of textures.
<ul> <li>Equipment Housings</li> <li>Miscellaneous Applications</li> </ul>
<ul> <li>Offered in thicknesses 0.71mm (0.028") and up</li> <li>Available in rollstock at 1.00mm (0.040") and in sheet stock in all thicknesses</li> <li>Available in black only</li> <li>Available in 7 distinctive textures</li> <li>Excellent forming properties, uniform wall thicknesses and crisp detail</li> <li>Easy machining and fabricating using conventional methods and equipment</li> </ul>
SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: http://www.sekisui-spi.com. For Material Safety Data Sheets, please call 800.325.3133.



88 Long Hill Cross Road, Shelton, Connecticut 06484 USA

ModernPlastics.com

sales@modernplastics.com

National Toll-Free: 800.243.9696

Phone: 203.333.3128

Fax: 203.333.4625

## **Technical Data Sheet**



KYDEX<sup>®</sup> V Utility sheet

## Physical Properties

Property	Test Method	Typical Value <sup>1</sup>	
Specific Gravity	ASTM D-792	1.35	
Tensile Strength	ASTM D-638	42 MPa	6,100 psi
Flexural Strength	ASTM D-790	63 MPa	9,100 psi
Modulus of Elasticity	ASTM D-790	2,308 MPa	335,000 psi
Notched Izod Impact Resistance, @ 23°C (73°F)	ASTM D-256	427 J/m	8 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	88	
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	73.9°C	165°F
Thermoforming Range		163 - 200°C	325 - 392°F
Mold Shrinkage % (male mold)		0.40 - 0.60	
1 Values based upon 3.18mm (0.125") sheet unless otherwise specified. Not intended for specification purposes.			



ISO 9001:2008 and ISO 13485:2003 Certifie

88 Long Hill Cross Road, Shelton, Connecticut 06484 USA

ModernPlastics.com

sales@modernplastics.com

National Toll-Free: 800.243.9696

Phone: 203.333.3128

Fax: 203.333.4625

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical property table technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY ON FITNESS FOR A PARTICULAR USE, EITHER EVPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions to use our products. The infringment of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.