



Makrolon® WG sheet

Window grade

Makrolon® WG polycarbonate engineering plate is an amorphous thermoplastic sheet. It offers extremely high impact strength, high modulus of elasticity, outstanding dimensional stability, and good mechanical and electrical properties. Makrolon WG demonstrates low levels of black specks or other impurities.

Applications

Sight windows for tanks/vessels, viewport windows, medical parts, military applications

Typical Properties			
Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D 792	-	1.2
Water Absorption, 24 hours @ 73°F	ASTM D 570	%	0.15
Poisson's Ratio	ASTM E 132	-	0.38
Haze	ASTM D 1746	%	1
MECHANICAL			
Tensile Strength, Break	ASTM D 638	psi	9,500
Tensile Strength, Yield	ASTM D 638	psi	9,000
Tensile Modulus	ASTM D 638	psi	340,000
Elongation	ASTM D 638	%	110
Flexural Strength	ASTM D 790	psi	13,500
Flexural Modulus	ASTM D 790	psi	345,000
Compressive Strength	ASTM D 695	psi	12,500
Compressive Modulus	ASTM D 695	psi	345,000
Shear Strength, Break	ASTM D 732	psi	10,000
Shear Strength, Yield	ASTM D 732	psi	6,000
Shear Modulus	ASTM D 732	psi	114,000
Rockwell Hardness	ASTM D 785	-	M70 / R118
THERMAL			
Coefficient of Thermal Expansion	ASTM D 696	in/in/°F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C 177	BTU-in/hr-ft ² -°F	1.35
Heat Deflection Temperature @ 264 psi	ASTM D 648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D 648	°F	280
Brittleness Temperature	ASTM D 746	°F	-200
ELECTRICAL			
Dielectric Constant @ 10 Hz	ASTM D 150	-	2.96
Dielectric Constant @ 60 Hz	ASTM D 150	-	3.17
Volume Resistivity	ASTM D 257	Ohm-cm	8.2 x 10 ¹⁶
Dissipation Factor @ 60 Hz	ASTM D 150	-	0.0009
Dielectric Strength, in air @ 0.125"	ASTM D 149	V/mil	380
FLAMMABILITY			
Flame Class @ 0.395"	UL 94	-	V-0

Agency and specification compliance

Polycarbonate sheet classification	A-A-59502	Type 1, Class 1
Polycarbonate resin classification	ASTM D 3935	PC0116
Flammability - Plastic component	UL 94	UL File #E351891

Makrolon® WG sheet

Fabrication guidelines

Cutting: A circular saw blade with carbide teeth utilizing the “triple chip” tooth design is the preferred method of cutting Makrolon WG polycarbonate sheet. Table or overhead panel saws are normally used. Circular saws should be run in the speed range of 6000-8000 ft/min. Blades for cutting 3/32” and thicker material should have 3-5 teeth per inch. The hook or rake angle should be 10°-15°.

Cautions

The following are suggested guidelines or concerns regarding machining working with Makrolon WG polycarbonate sheet or any other engineering plastics.

1. Thermal expansion is up to 10 times greater with plastics than metals
2. Plastics will lose heat more slowly than metals
3. Avoid localized overheating
4. Softening/melting temperatures of plastics are much lower than metals

MODERN *plastics*

“Setting the Standards in Plastics Distribution”™

ISO 9001:2008 and ISO 13485:2003 Certified

88 Long Hill Cross Road, Shelton, Connecticut, 06484 USA

ModernPlastics.com - National Toll-Free: 800.243.9696

Phone: 203.333.3128 - Fax: 203.333.4625

sales@modernplastics.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.