

Makrolon® DX-NR sheet

Polycarbonate diffuser sheet for outdoor LED lighting

Makrolon DX-NR is a translucent polycarbonate product specifically designed for use as a lighting lens in outdoor applications. The diffuser technology helps to provide uniform luminance and ensures elimination of LED hot spots while maintaining high light transmission. The advanced UV resistance technology provides long lasting weathering performance and the non-reflective texture built into the UV resistant side of the sheet, enhances its aesthetics.

When compared to other light diffusing products such as glass and acrylic, Makrolon DX-NR has superior impact strength and toughness. Its higher flammability resistance and wider service temperature provide an additional advantage over acrylic diffusers.

| Typical Properties* | | | |
|---------------------------------------|-------------------|------------------|-------------------------|
| Property | Test Method | Units | Values |
| PHYSICAL | | | |
| Specific Gravity | ASTM D 792 | - | 1.2 |
| Water Absorption, 24 hrs | ASTM D 570 | % | 0.15 |
| Poisson's Ratio | ASTM E 132 | - | 0.38 |
| Light Transmission @ 0.060" / 0.118" | ASTM D 1003 | % | 69 / 61 |
| Light Diffusion @ 0.060" / 0.118" | FWHM | degrees | 150 / 152 |
| MECHANICAL | | | |
| Tensile Strength, Ultimate | ASTM D 638 | psi | 9,500 |
| Tensile Strength, Yield | ASTM D 638 | psi | 9,000 |
| Tensile Modulus | ASTM D 638 | psi | 340,000 |
| Elongation | ASTM D 638 | % | 110 |
| Flexural Strength | ASTM D 790 | psi | 13,500 |
| Flexural Modulus | ASTM D 790 | psi | 345,000 |
| Instrumented Impact @ 0.118" | ASTM D 3763 | ft·lbs | 47 |
| THERMAL | | | |
| Coefficient of Thermal Expansion | ASTM D 696 | in/in/°F | 3.75 x 10 ⁻⁵ |
| Coefficient of Thermal Conductivity | ASTM C 177 | BTU-in/hr-ft2-°F | 1.35 |
| Heat Deflection Temperature @ 264 psi | ASTM D 648 | °F | 270 |
| Heat Deflection Temperature @ 66 psi | ASTM D 648 | °F | 280 |
| ELECTRICAL | | | |
| Dielectric Constant @10 Hz | ASTM D 150 | - | 3.0 |
| Dielectric Constant @ 60 Hz | ASTM D 150 | - | 3.2 |
| Volume Resistivity | ASTM D 257 | Ohm·cm | >8 x 10 ¹⁵ |
| FLAMMABILITY | | | |
| Flame Class @ 0.060" | UL 94 | - | V2** |
| @ 0.118" | UL 94 | - | HB** |
| Glow Wire Flammability Index | DIN EN 60695-2-12 | °F | 1560 |
| Glow Wire Ignition Test | DIN EN 60695-2-13 | °F | 1607 |

^{*}Typical Properties are not intended for specification purposes



^{**}Test results, product not UL 94 Listed



"Setting the Standards in Plastics Distribution"™
ISO 9001:2008 and ISO 13485:2003 Certified

88 Long Hill Cross Road, Shelton, Connecticut, 06484 USA ModernPlastics.com - National Toll-Free: 800.243.9696 Phone: 203.333.3128 - Fax: 203.333.4625

sales@modernplastics.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without varranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.