



"Setting the Standards in Plastics Distribution"™

ISO 9001:2000 Certified

678 Howard Ave.
Bridgeport, CT 06605
National Toll Free: 800.243.9696

KYDEX®

100AS

ANTI-STAT SHEET

General Information

KYDEX 100AS, a proprietary alloy sheet, brings new dimensions to anti-static protective materials in: formability, rigidity, breakage resistance, and chemical resistance. This sheet is available in standard and custom gauges from .028" (.71mm) and up, in many distinctive textures and hundreds of colors. Unlike other anti-static thermoplastic sheets, KYDEX 100AS retains its anti-static properties even after thermoforming. It has a surface resistivity of 109 to 1012 Ohms/square.

Features

Anti-Static Properties: Unlike other anti-static thermoplastic sheets, KYDEX 100AS retains its anti-static properties even after thermoforming. Also it is available in a multitude of colors.

Superior Formability: For deep or hard to form parts or where good finished detail is required, KYDEX 100AS is unsurpassed.

Breakage Resistance: With a high notched Izod Impact resistance, KYDEX 100 AS offers superior resistance to breakage.

Chemical Resistance: KYDEX meets the highest standard for chemical resistance

Thermoformability: Excellent forming properties results in uniform wall thicknesses and crisp detail, plush easy machining and fabricating using conventional methods, further expanding finished part possibilities.

RIPH: KYDEX is endorsed by the Royal Institute of Public Health for conformance to the standard of Hygienic Merit

Offering superior impact resistance and flame resistance in an anti-static sheet.

| Property | Test Method | Typical Value ¹ |
|----------------------------------------------------------------|-----------------------------|-----------------------------------|
| Specific Gravity | ASTM D-792 | 1.33 |
| Tensile Strength | ASTM D-638 | 5780 psi (35-41 MPa) |
| Flexural Modulus | ASTM D-790 | 9,780 psi (62-69 MPa) |
| Modulus of Elasticity | ASTM D-790 | 347,000 psi (2206-2344 MPa) |
| Notched Izod Impact Resistance @ 73° F (23° C) | ASTM D-256 | 16 ft-lbs/in (846 J/m) |
| Surface Resistivity, Ohms/square | ASTM D-257 | 10 ⁹ -10 ¹² |
| Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed | ASTM D-648 | 167° F (67.2° C) |
| Flammability: Underwriter's Lab. Component Recognition | UL Standard 94 ² | V-0 > 0.038" (1 mm) |
| Forming Temperature | | 325-390° F (163-200° C) |

¹All Values are based upon 0.125" (3.12 mm) sheet unless otherwise specified.

²Underwriter's Laboratories Inc., File E115252
Not intended for specification purposes.



"Setting the Standards in Plastics Distribution"™

ISO 9001:2000 Certified

678 Howard Ave.
Bridgeport, CT 06605
National Toll Free: 800.243.9696

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users of our products should make their own tests to determine the suitability of each product for their particular purposes. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE, and buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Kydex® is a registered trademark of Kleeindex Company. ©2001 Kleeindex Company.