

HYDLAR ® Z - Stock Shapes

Chemical Designation

PA 66 (Polyamide 66)

Colour

yellow-brown

Density

1.16 g/cm³

Fillers

aramide fibres

Main features

- excellent wear properties
- excellent strength and stiffness
- minimizes mating surface abrasion
- easy to machine
- high mechanical load capacity

Target Industries

- construction industry
- conveyor technology
- gear manufacturing
- power engineering
- mechanical engineering

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)		1,300,000	psi	ASTM D 638	1) (1) Injection molded samples 2) Injection molded samples
Tensile strength		16,000	psi	ASTM D 638	2)
Elongation at break		4	%	ASTM D 638	
Flexural strength		23,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)		900,000	psi	ASTM D 790	
Compression strength		19,300	psi	ASTM D 695	
Impact strength (Izod)		2.7	ft-lbs/in	ASTM D 256	
Wear rate	ASTM Thrust Washer Test @ PV=2,500	79-128		ASTM D 3702	
Thermal properties	condition	value		test method	comment
Deflection temperature	@264 psi	470	°F	ASTM D 648	(1) Data obtained from public source
Service temperature	Intermittent	300	°F	-	
Service temperature	Long Term	200	°F	-	1)
Thermal expansion (CLTE)		1.6*10 ⁻⁵	in/in/°F	ASTM D 696	
Other properties	condition	value		test method	comment
Limiting PV	P=250 PSI; V=10 ft/min	2,500	psi-fpm	ASTM D 3702	
Moisture absorption	@ 24 hrs, 73 °F	0.8	%	ASTM D 570	
Moisture absorption	@ saturation, 73 °F	6.3	%	ASTM D 570	

→ Resin specification:
ASTM D6779-11 PA0100 and ASTM D4066-01a (Reapproved 2008) PA0110
Shapes specification:
ASTM D 5989-11 S-PA0101R3050000000

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensinger-inc.com.