

Mitsubishi Chemical Advanced Materials Nylatron® GS Nylon, Extruded MoS2 Filled Type 66 (ASTM Product Data Sheet)
Categories: Polymer; Thermoplastic; Nylon (Polyamide PA); Nylon 66 (PA66); Nylon 66, MoS2 Filled

Material Notes: Quadrant Engineering Plastic Products is now Mitsubishi Chemical Advanced Materials.

Key Words: Polyamide 66; PA66; PA 66; Polyamide 6/6; Polyamide 6,6; Nylon 6/6; Nylon 6,6

Physical Properties	Metric	English	Comments
Specific Gravity	1.16 g/cc	1.16 g/cc	ASTM D792
Water Absorption	0.30 %	0.30 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	7.0 %	7.0 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	85	85	ASTM D785
Hardness, Rockwell R	115	115	ASTM D785
Hardness, Shore D	85	85	ASTM D2240
Tensile Strength	86.2 MPa	12500 psi	ASTM D638
Tensile Strength at 65°C (150°F)	41.4 MPa	6000 psi	ASTM D638
Elongation at Break	25 %	25 %	ASTM D638
Tensile Modulus	3.31 GPa	480 ksi	ASTM D638
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	3.17 GPa	460 ksi	ASTM D790
Compressive Strength	110 MPa	16000 psi	10% Def.; ASTM D695
Compressive Modulus	2.90 GPa	420 ksi	ASTM D695
Shear Strength	72.4 MPa	10500 psi	ASTM D732
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.20	0.20	Dry vs. Steel; QTM55007
K (wear) Factor	181 x 10 ⁻⁸ mm ³ /N-M	90.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.105 MPa-m/sec	3000 psi-ft/min	4:1 safety factor; QTM 55007

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11
Dielectric Strength	13.8 kV/mm	350 kV/in	Short Term; ASTM D149

Thermal Properties	Metric	English	Comments
CTE, linear	72.0 µm/m-°C @Temperature -40.0 - 149 °C	40.0 µin/in-°F @Temperature -40.0 - 300 °F	ASTM E831
Thermal Conductivity	0.245 W/m-K	1.70 BTU-in/hr-ft ² -°F	ASTM F433
Melting Point	260 °C	500 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	104 °C	220 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	ASTM D648
Flammability, UL94	V-2 @Thickness 3.17 mm	V-2 @Thickness 0.125 in	Estimated Rating

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Unacceptable	Unacceptable	
Acids, Weak	Limited	Limited	
Alcohols	Limited	Limited	
Alkalies, Strong (pH 11-14)	Unacceptable	Unacceptable	
Alkalies, Weak	Limited	Limited	
Chlorinated Solvents	Limited	Limited	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	

Hydrocarbons - Aromatic	Acceptable	Acceptable
Inorganic Salt Solutions	Acceptable	Acceptable
Ketones, Esters	Acceptable	Acceptable

Descriptive Properties

Color	Black-Grey	
Machinability	1	1-10, 1=Easier to Machine